

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 63149356
PUBLICATION DATE : 22-06-88

APPLICATION DATE : 15-12-86
APPLICATION NUMBER : 61296680

APPLICANT : RES INST ELECTRIC MAGNETIC ALLOYS;

INVENTOR : MURAKAMI YUETSU;

INT.CL. : C22C 38/30 C21D 6/00 C22C 38/00 C22C 38/32 H01F 1/14 H01H 1/66 H01H 11/04

TITLE : SOFT MAGNETIC ALLOY FOR REED CHIP, MANUFACTURE THEREOF AND REED SWITCH

ABSTRACT : PURPOSE: To manufacture an alloy suitable for use as a material for the reed chip of a reed switch by adding specified percentages of Co, Cr, Mo, V, Nb, W and Ta to Fe so as to provide specified magnetic flux density and coercive force to the resulting soft magnetic alloy.

CONSTITUTION: An alloy consisting of, by weight, 20-65% Co, 0.01-10% in total of one or more among $\leq 5\%$ each of Cr, Mo, V and Nb and $\leq 10\%$ each of W and Ta and the balance Fe with a small amt. of impurities is manufactured. The alloy is cold worked at \geq about 50% working rate and heated at \geq about 700°C to obtain a soft magnetic alloy having $\geq 16\text{kG}$ magnetic flux density and $\leq 2\text{Oe}$ coercive force in 50Oe magnetic field. The alloy also has low specific electric resistance and a low coefft. of thermal expansion, so it is suitable for use as a material for the reed chip of a reed switch.

COPYRIGHT: (C)1988,JPO&Japio